



COLORADO® UV SOLAR CONTROL

COLORADO® UV SOLAR CONTROL sheet is developed for applications where heat or Solar Radiation is reflected or absorbed providing low heat build up, good light transmission and ambiance. The Solar control product provides heat build up protection hence used for applications to reduce air conditioning costs.

COLORADO® UV SOLAR CONTROL has a unique colour tint which allows the sheet to have outstanding transparency or clarity. The surface quality is superior due to our line capabilities to control the distribution of the UV protection layer.

ALSO AVAILABLE as Saphir Colorado (Hard Coated, scratch resistant).

EXCELLENT FIRE PERFORMANCE complying requirements to EN 13501-1 (EUROPEAN BUILDING STD). In case of fire, the sheet will melt and allow venting where heat and smoke will be let out and therefore reduce the growth of fire by flame spread.

COLORADO® UV SOLAR CONTROL BENEFITS:

- The sheet absorbs IR heat and creates a stable indoor climate
- More than 10 times the impact strength of high impact PMMA
- Easy to thermoform or fabricate
- Half the weight of glass
- Two sides UV as standard

APPLICATION AREAS:

Building industry roofing, cladding, sidewalls, conservatories, domes, skylights, sheds, car ports, smoke vents, swimming pool covers, glasshouses, shoppingcentre roofing, railway/metro station and stadia roofing. Agriculture greenhouses, lorry/tractor ports and farm/barn buildings.

DELIVERY PROGRAM:

Standard size: 2050 x 3050 mm

Thickness range: 3 – 8 mm

Colour: SG 63, SG 74, Blue, Grey and Bronze

Special sizes and thicknesses on request

COLORADO® SOLAR CONTROL TECHNICAL SPECIFICATIONS

Property	Value	Unit	Standard
Physical properties			
Density	1,2	g/cm ³	ISO 1183
Refractive index (20 °C)	1,586		ISO 489
Moisture absorption 24 hours, 23 °C, 50% RH	0,15	%	ISO 62
Mechanical properties			
Tensile strength at yield (at break)	60 (70)	N/mm ²	ISO 527
Elongation at yield (at break)	6 (110)	%	ISO 527
Elastic modulus	>2300	N/mm ²	ISO 527
Flexural modulus	>2300	N/mm ²	ISO 178
Charpy unnotched impact strength -40 °C	NB	kJ/m ²	ISO 179/1eU
Charpy notched impact strength -30 °C	11	kJ/m ²	ISO 179/1eA
Izod notched impact strength +23 °C	65	kJ/m ²	ISO 180/1A
Izod notched impact strength -30 °C	10	kJ/m ²	ISO 180/1A
Thermal properties			
Linear coefficient of thermal expansion (20-70 °C)	65x10 ⁻⁶	K ⁻¹	ISO 11359-2
Heat deflection temperature, HDT A (1,80 N/mm ²)	132	°C	ISO 75
Heat deflection temperature, HDT B (0,45 N/mm ²)	142	°C	ISO 75
Vicat temperature VST/B 120	149	°C	ISO 306
Vicat temperature VST/B 50	148	°C	ISO 306
Thermal conductivity	0,20	W/m.K	DIN 8302
Electrical properties			
Volume resistivity, dry	>10 ¹⁴	Ω . m	IEC 60093
Surface resistivity, dry	10 ¹⁶	Ω	IEC 60093
Dielectric strength, dry	30	kV/mm	IEC 60243
Dielectric constant, dry 50 Hz	3		IEC 60250
Dielectric constant, dry 1 MHz	2,9		IEC 60250
Dissipation factor (tan δ), dry 50 Hz	0,001		IEC 60250
Dissipation factor (tan δ), dry 1 MHz	0,01		IEC 60250
Spectral properties			
Light transmittance Tv			
3 mm SG 63	63	%	ASTM D1003
3 mm SG 74	74	%	ASTM D1003
3 mm Blue	62	%	ASTM D1003
3 mm Grey	62	%	ASTM D1003
3 mm Bronze	68	%	ASTM D1003
Total solar energy transmittance g			
3 mm Grey	68	%	EN 14500
3 mm Bronze	68	%	EN 14500
3 mm Blue	66	%	EN 14500
3 mm Green SG 63	51	%	EN 14500
3 mm Green SG 74	63	%	EN 14500

Properties reported here are typical values. Arla Plast makes no representation that the material in any particular shipment will conform exactly to the values given. The above information is based upon experience and given in good faith. Due to many factors which are outside our knowledge and control, no warranty is given or is to be implied with respect to such information. Detailed product specification and technical manual/information is available on request.